



SPEC

DATA

This Spec-Data Sheet conforms To the editorial style prescribed by The Construction Specifications Institute. The manufacturer is Responsible for technical accuracy.

1. PRODUCT NAME

MASTERKRETE TILE GROUT

2. MANUFACTURER

HARRICRETE LIMITED

Las Lomas #2
Republic of Trinidad & Tobago
Tel: (868) 669-4011/4037
Fax: (868) 669-1035
E-mail: hcrete@tstt.net.tt
Website: www.harricrete.com

3. PRODUCT DESCRIPTION

Harricrete Masterkrete Tile Grout, is an accurately blended mixture of bleached white processed sands, Portland cement, chemical admixtures and the finest quality colour pigments. This chemically modified cementitious grout was specifically designed to easily work into pointing areas, with very high cohesive and adhesive bond strengths. Unlike regular cementitious pointing materials, this grout is non-shrink thereby creating a firm bond between pointing spaces.

Masterkrete Tile Grout is also water repellent, so when applied to tile joints moisture will not soak in between the tiles to encourage the growth of mould, mildew and fungus. A wide range of colored pigments offers a variety of standard colours to match any tile, stone or brick work. For interior and exterior areas. The result is long lasting beauty and value.

3. PRODUCT BENEFITS/ADVANTAGES

- ❖ Extremely high bond strength
- ❖ Non-shrink
- ❖ Water Repellent
- ❖ Reduces Mildew and Fungus growth
- ❖ Colours can be matched for almost any tile.

4. DIRECTIONS FOR USE:

All pointing spaces should be clean, dry and free from loose dirt, dust and other contaminants that will prevent effective bonding.

1. Add water to grout and mix for about five (5) minutes until a smooth buttery consistency is achieved.

(NB) Initial mixing of water into grout may require constant mixing. Do not add too much water in the initial stage of mixing.

2. Apply to joints and allow 45 minutes to 1 hour for initial set. Clean off tiles thoroughly after initial set.

3. Using damp cloth or sponge float, ensure tiles are thoroughly cleaned before final set 4 to 5 hours.

5. COVERAGE

Using a ¼ notch trowel
25 sq. ft. per 5lb bag
125 sq. ft. per 25lb bag
250 sq. ft. per 50lb bag

6. CAUTION

If a material sets before using, do not add more water to remix. Fresh mixture should be made.

7. AVAILABILITY

For sanded and unsanded applications in 5lb, 25lb and 50lb Packages.

8. TECHNICAL SERVICES

Harricrete Ltd. offers consultancy service for architects and engineers covering specifications architectural detail and technical field services.