



## 1. PRODUCT NAME

SACRETE

### MANUFACTURER

**HARRICRETE LIMITED**  
Jankie Trace, Las Lomas #2  
Republic of Trinidad and Tobago.  
Tel: (868) 669-4011/4037  
Fax: (868) 669-1035  
E-mail: harricreteltd@gmail.com  
Website: [www.harricrete.com](http://www.harricrete.com)

At a constant

### COMPRESSIVE STRENGTH:

28 days --30 to 33 MN/ m.2 (4200 to 4700 psi) Using 2.9 to 3 litres of water per bag (11% by weight)

### NOTE:

Shading and Moist curing are recommended to avoid shrinkage cracking of all Portland Cement Mixes.

## 2. PRODUCT DESCRIPTION

Sacrete is a high strength, tough concrete mix consisting of ½” gravel, coarse sand and Portland cement.

## 3. RECOMMENDED FOR:

Any general concrete work e.g. Floors, footpaths, fenceposts, foundations, driveways etc.

## 4. FEATURES/BENEFIT:

- Easy to use. Just add water.
- Manufactured to rigorous Quality Control standards and ASTM specifications.

## 5. PACKAGING /COVERAGE/ YIELD:

Sacrete is packaged in a 50lb bag.  
**YIELD: 0.45 CU. FT. – 0.0135 cu. metre. (56 bags per cu. Yd. / 75 bags per cu. Metre.**  
**COVERAGE:**  
3 sq.ft. – 2” thick OR ¼ sq.mtre-5cm thick  
2 sq.ft. – 3” thick OR 1/6 sq. mtre-7.5 cm thick  
1 ½ sq. ft. -4” thick OR 1/8 sq. mtre – 10cm thick

**SPEC**  
**DATA**

This Spec-Data Sheet conforms To the editorial style prescribed by The Construction Specifications Institute. The manufacturer is Responsible for technical accuracy